



Ddev Plastiks Industries Limited

TECHNICAL DATA SHEET

KI – 13 K LT (-40): PVC cable compound for low temperature insulation application

Description:

KI – 13 K LT (-40) is insulation type compound for low temperature insulation applications in a wide variety of cables. **KI – 13 K LT (-40)** is formulated with a high-quality resin with plasticizers, stabilizers and other additives.

Specification:

- IS 5831: 2001 Type A
- BS EN 50363-3 TI 4

Colour: Natural/as per requirement

Typical Properties:

Property	Unit	Test Method	Typical Value
Application temperature			(+) 75°C to (-) 40°C
Sp. Gravity @27°C		ASTM - D – 792	1.40 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	85 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60)	≥ 100
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7)	≥ 14.0
Elongation at Break (E.B) @27°C	%	IS : 10810 (7)	≥ 250
Ageing Test	Temperature	°C	80
	Duration	Hr	168
Variation of T.S	%	IS : 10810 (11)	≤ ± 20.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 20.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 1.5
Volume Resistivity @27°C	Ohm - cm	IS : 3396 / 79	≥ 5x10 ¹³

Passes Cold Bend & Cold Impact @-40°C

* Test specimen made after milling the granules and then in compression mould at 160 °C for 10 min with 200kg/cm² hydraulic pressure

Above Values are Typical value of Compound and customer need to check before accepting the TDS.

Processing:

KI – 13 K LT (-40) can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 140°C- 170°C. This is the guideline temperature range; actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 70+/-5°C is always advisable for better processing.

Packaging:

KI – 13 K LT (-40) is available in the form of free-flowing pellets and supplied in bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage and Shelf Life:

Material should be store in moisture free cool & dry place and should be consume within three months.

Safety:

KI – 13 K LT (-40) is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:

2B Pretoria Street, Kolkata-71
Tel: 91-33-22823744/45/3671
Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in

Website: www.ddevgroup.in

Works:

Survey No: 24/3, Demni Road, Village-Demni
Dadra(Dadra & Nagar Haveli)-396 193, India
[Tel:91-9909006426](tel:91-9909006426)

E-mail:dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate
New Link Road, Andheri(West)
Mumbai-400053, India

E-mail: mumbai@ddevgroup.in