



# Ddev Plastiks Industries Limited

## TECHNICAL DATA SHEET

### **KI – 40 (RoRE) LT (-30): Sheathing Type Flame Retardant PVC Cable Compound (Flexible application)**

#### **Description:**

**KI – 40 (RoRE) LT (-30)** is Flame Retardant PVC Compound for flexible Sheathing applications in a wide variety of cables. It is formulated with a high-quality suspension grade PVC resin with suitable plasticizers, stabilizers, flame retardant chemicals and other additives. The compound will meet the RoHS & REACH compliance norms.

#### **Specification:**

IS 5831: 2001 Type ST1

#### **Typical Properties:**

Property	Unit	Test Method	Typical Value
Application Temp.	<sup>0</sup> C		+70 to -30
Sp. Gravity @27 <sup>0</sup> C		ASTM - D – 792	1.45± 0.03
Hardness @27 <sup>0</sup> C	Shore A	ASTM - D 2240	84 ± 2
Thermal Stability@200 <sup>0</sup> C	Minutes	IS : 10810 (60)	≥ 70
Tensile Strength (TS) @27 <sup>0</sup> C	MPa	IS : 10810 (7)	≥ 14.0
Elongation at Break (E.B) @27 <sup>0</sup> C	%	IS : 10810 (7)	≥ 250
Ageing Test	Temperature	<sup>0</sup> C	80
	Duration	Hr	168
Variation of T.S	%	IS : 10810 (11)	≤ ± 20.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 20.0
Mass Loss on Ageing	mg/cm <sup>2</sup>	IS : 10810 (10)	≤2.00

Passes Cold Bend & Cold Impact @-30<sup>0</sup>C

\* Test specimen made after milling the granules and then in compression mould at 160<sup>0</sup>C for 10 min with 200kg/cm<sup>2</sup> hydraulic pressure

**Colour:** Natural

#### **Processing:**

**KI – 40 (RoRE) LT (-30)** can be processed on any good extruder designed for PVC compound extrusion at temperature in the range of 130<sup>0</sup>C- 160<sup>0</sup>C. This is the guideline temperature range, actual temperature should be determined by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 70+/-5<sup>0</sup>C for 15minutes is always advisable for better processing.

#### **Packaging:**

**KI – 40 (RoRE) LT (-30)** is available in the form of free-flowing pellets and supplied in 25 Kg woven sack bags with sealed double layer PE liner to prevent moisture or in 1000kg jumbo bags.

#### **Storage and Shelf Life:**

Material should be store in moisture free cool & dry place and should be consume within three months from the date of manufacturing.

#### **Safety:**

**KI – 40 (RoRE) LT (-30)** is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

#### **Head Office:**

2B Pretoria Street, Kolkata-71  
Tel: 91-33-22823744/45/3671  
Fax:91-33-22823739

E-mail: [kolkata@ddevgroup.in](mailto:kolkata@ddevgroup.in)

Website: [www.ddevgroup.in](http://www.ddevgroup.in)

#### **Works:**

Survey No: 24/3, Demni Road, Village-Demni  
Dadra( Dadra & Nagar Haveli)-396 193, Indiam

Tel:91-9909006426

E-mail:[dadra@ddevgroup.in](mailto:dadra@ddevgroup.in)

#### **Mumbai Office**

106, Laxmi Plaza, Laxmi Industrial Estate  
New Link Road, Andheri(West)  
Mumbai-400053, India

E-mail: [mumbai@ddevgroup.in](mailto:mumbai@ddevgroup.in)