



Ddev Plastiks Industries Limited

TECHNICAL DATA SHEET

KI – 73 L: PVC cable compound for transparent application

Description:

KI – 73L is sheathing & Insulation compound for transparent applications in a wide variety of cables. **KI –73 L** is formulated with high quality resin, plasticizers, stabilizers and other additives.

Specification:

- IS 5831: 2001 Type ST1 & Type D
- BS 7655:TM – 2

Typical Properties:

Property	Unit	Test Method	Typical Value
Sp. Gravity @27°C		ASTM - D – 792	1.24 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	74 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60)	≥ 45
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7)	≥ 13.5
Elongation at Break (E.B) @27°C	%	IS : 10810 (7)	≥ 250
Ageing Test	Temperature	°C	80 / 70
	Duration	Hr	168
Variation of T.S	%	IS : 10810 (11)	≤ ± 20.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 20.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 2.0
Volume Resistivity @27°C	Ohm - cm	IS : 3396 / 79	≥ 1x10 ¹³

* Typical values reported in the table have been obtained from measurements made on compression moulded sheet. Above Values are Typical value of Compound and customer need to check before accepting the TDS.

Processing:

KI – 73L can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 130°C- 170°C.This is the guideline temperature range; actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 60+/-5°C for 10mins is always advisable for better processing.

Packaging:

KI – 73L is available in the form of free-flowing pellets and supplied in bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage and Shelf Life:

Material should be store in moisture free cool & dry place and should be consume within three months from the date of manufacturing.

Safety:

KI – 73L is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:

2B Pretoria Street, Kolkata-71

Tel: 91-33-22823744/45/3671

Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in

Website: www.ddevgroup.in

Works:

Survey No: 24/3, Demni Road, Village-Demni

Dadra (Dadra & Nagar Haveli)-396230, India

Tel:91-9909006426

E-mail: dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate

New Link Road, Andheri (West)

Mumbai-400053, India

E-mail: mumbai@ddevgroup.in