

## TECHNICAL DATA SHEET

### KI-38S FRLS (ST-2)

**DESCRIPTION :** KI-38S FRLS (ST-2) IS FLAME RETARDENT PVC COMPOUND MEET IS-5831- 2001(TYPE-ST-2) FOR WIRE & CABLE APPLICATION.

#### **SPECIAL CHARACTERISTICS :**

- Excellent surface smoothness .
- Better mechanical properties and dimensional stability
- Long run Extrusion without Thermal degradation
- Excellent physical and thermal property.
- Balances of properties and processability.

#### **SPECIFICATION :**

1. This compound will meet type-ST2 of IS-5831
2. KI-38 FRLS (ST-2) Compound will meet the special properties like:
  - i) Limiting Oxygen Index (ASTM D 2863)
  - ii) Temperature Index (ASTM D 2863)
  - iii) Acid gas generation (IEC -754-1)
  - iv) FIRE RESISTANCE TEST AS PER:
    - a) IEC-332-3,CATEGORY A,B & C
    - b) IEEE-383
    - c) SS 424 14 75 (Swedish chimney Test)

Properties	Unit	Requirement IS 5831 Specification	Typical value*
Specific gravity	-	NOT APPLICABLE	1.52 ± 0.02
Shore hardness	“A”	NOT APPLICABLE	92± 2
<b>Before Ageing</b>			
Tensile strength	N/mm <sup>2</sup>	12.5 (min)	≥ 15.0
Elongation at break	%	150 (min)	≥ 225
<b>After ageing @ 80°C ± 2°C for 7 days</b>			
Variation in Tensile strength	%	± 25(max)	± 10
Variation in Elongation	%	± 25(max)	± 10
Thermal Stability @ 200°C ± 0. 5°C	Minutes	80 (min)	150
<b>Loss Of Mass In Air Oven @ 80°C ± 2°C for 7 days</b>			
Loss Of Mass	Mg/cm <sup>2</sup>	2 (max)	0.6
<b>FRLS TEST</b>			
Oxygen index	%	29 (min)	32
Temperature index	° C	250 (min)	≥ 275
Smoke density	%	60 (max)	52
Light Transmission	%	40(min)	48
HCL Emission	%	20 (max)	18

\*\* The properties have been tested on moulded sheet

**PROCESSING TECHNIQUES:**

1. The recommended processing temperatures are 150<sup>0</sup>c to 180<sup>0</sup>c , However the processing Temperature may be adjusted as per requirement for individual operations.
2. The PVC compounds provides excellent surface finish and outstanding output rates over a broad range of extrusion running condition .
3. For smooth processing and better results it is recommended to preheat the material before use.

**DELIVERY/PACKAGES :** Pellet form and packed in 25 kg HDPE woven sacks with inner liner to ensuring prevention from uptake of moisture and contamination.

**STORAGE:**

Material shall be kept in a cool dry place.

(The information given in the document is believed to be reliable and is given in good faith but without warranty. The user should test the product to assertion the suitability for intended use. The product specification or the whole document is subject to change without any prior notice.)

**FOR MORE INFORMATION PL CONTACT AT :**

**Head Office:**  
2B Pretoria Street, Kolkata-01  
Tel: 91-33-22823744/45/3671  
Fax:91-33-22823739  
E-mail: [kolkata@ddevgroup.in](mailto:kolkata@ddevgroup.in)  
Website: [www.ddevgroup.in](http://www.ddevgroup.in)

**Works:**  
Survey No: 24/3, Demni Road, Village-Demni  
Dadra( Dadra & Nagar Haveli)-396230, India  
Tel:91-260-2668 758/59/61,Fax:91-260 2668760  
E-mail:[dadra@ddevgroup.in](mailto:dadra@ddevgroup.in)

**Mumbai Office**  
106, Laxmi Plaza, Laxmi Industrial Estate  
New Link Road, Andheri(West)  
Mumbai-400053, India  
E-mail: [mumbai@ddevgroup.in](mailto:mumbai@ddevgroup.in)

168-151-158, Dabhel Industrial Co-Op Soc. Ltd  
Dabhel, Daman-369215  
Tel: 91-260-2242684/6545123, Fax: 91-260 2243799  
E-mail: [daman@ddevgroup.in](mailto:daman@ddevgroup.in)

**KOLKATA WORKS**  
Vill &P.O:Chaturbhujkathi, kandua,  
P.S.Sankarail, howrah-711313  
E-mail: [kolkata@ddevgroup.in](mailto:kolkata@ddevgroup.in)