

Ddev Plastiks Industries Limited

TECHNICAL DATA SHEET



KI – 90 FR ROHS UV: Flame retardant PVC Cable Compound(TI-3 /TM3 as per BS 7655)

Description:

KI – 90 FR ROHS UV is a UV resistant flame retardant compound LEAD FREE for insulation applications in a wide variety of cables.

KI – 90 FR ROHS UV is formulated with a high quality resin with plasticizers, stabilizers and flame retardant chemicals & uv stabilizer .

Typical Properties:

Cable manufactured with **KI – 90 FR ROHS UV** according to standard manufacturing process meets BS: 7655 specification.

Property	Unit	Test Method	KI – 90FR ROHS UV
Sp. Gravity @27°C		ASTM - D – 792	1.49 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	92 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60)	≥ 140
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7)	≥ 15.0
Elongation at Break (E.B) @27°C	%	IS : 10810 (7)	≥ 200
Ageing Test	Temperature	°C	100
	Duration	Hr	168
Variation of T.S	%	IS : 10810 (11)	± 20.0
Variation of E.B	%	IS : 10810 (11)	± 20.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 1.2
Volume Resistivity @27°C	Ohm - cm	IS : 3396 / 79	≥ 1x10 ¹⁴
Limiting Oxygen Index	%	IS : 10810 (58)	≥ 29.0

* Test specimen made after milling the granules and the compression moulded at 160 °C for 10 min with 200kg / cm² hydraulic pressure

Processing:

KI – 90 FR ROHS UV can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 140°C- 180°C. This is the guideline temperature range, actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 80+/-5°C is always advisable for better processing.

Packaging:

KI – 90 FR ROHS UV is available in the form of free flowing pellets and supplied in bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage:

Material should be stored in moisture free cool & dry place.

Safety:

KI – 90 FR ROHS UV is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:
2B Pretoria Street, Kolkata-01
Tel: 91-33-22823744/45/3671
Fax: 91-33-22823739
E-mail: kolkata@ddevgroup.in
Website: www.ddevgroup.in

Works:
Survey No: 24/3, Demni Road, Village-Demni
Dadra(Dadra & Nagar Haveli)-396230, India
Tel: 91-260-2668 758/59/61, Fax: 91-260 2668760
E-mail: dadra@ddevgroup.in

168-151-158, Dabhel Industrial Co-Op Soc. Ltd
Dabhel, Daman-369215
Tel: 91-260-2242684/6545123, Fax: 91-260 2243799
E-mail: daman@ddevgroup.in

Mumbai Office
106, Laxmi Plaza, Laxmi Industrial Estate
New Link Road, Andheri(West)
Mumbai-400053, India
E-mail: mumbai@ddevgroup.in

KOLKATA WORKS
Vill & P.O: Chaturbhujkathi, kandua,
P.S.Sankarail, howrah-711313
E-mail: kolkata@ddevgroup.in