

KI-33 (E7): Low Smoke, Low Halogen, Flame Retardant PVC Cable Compound

Description:

KI-33 (E7) is Low Smoke, Low Halogen and Flame-Retardant Compound for Sheathing applications in a wide variety of cables. It is formulated with a high-quality resin with special plasticizer, stabilizers and flame-retardant chemicals. Smoke and HCL absorbers are added so that emission of smoke and HCL are limited to low levels when the cable burns.

Specification:

- IS 5831: Type ST2

Typical Properties:

Property	Unit	Test Method	Typical Value
Application Temp	°C		90°C
Sp. Gravity @27°C		ASTM - D – 792	1.55 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	93 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60) / EN 60811-3-2	> 100
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7) / EN 60811-1-1	> 14.0
Elongation at Break (E.B) @27°C	%	IS : 10810 (7) / EN 60811-1-1	> 200
Ageing Test	Temperature	IS: 5831	100±2
	Duration		168
Variation of T.S, Max.	%	IS : 10810 (11) / EN 60811-1-2	± 25.0
Variation of E.B, Max.	%	IS : 10810 (11) / EN 60811-1-2	± 25.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10) / EN 60811-3-2	<2.00
Limiting Oxygen Index	%	IS : 10810 (58)/ ASTM D 2863	>30
Temperature Index	°C	IS : 10810 (64)	>250
Smoke Density Rating	%	ASTM-D 2843	<58.0
Halogen Acid Gas Emission	%	IS : 10810 (59)/ IEC 60754-1	<20.0

* Test specimen made after milling the granules and then in compression moulded at 160 °C for 10 min with 200kg / cm² hydraulic pressure

Above Values are Typical value of Compound and customer need to check before accepting the TDS.

Color: Natural

Processing:

KI-33 (E7) can be processed on any good extruder designed for PVC at temperature in the range of 140°C- 180°C. This is the guideline temperature range; actual temperature should be determined by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 80+/-5°C for 10-15mins is always advisable for better processing.

Packaging:

KI-33 (E7) is available in the form of free-flowing pellets and supplied in green colour bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage:

Material should be store in moisture free cool & dry place and should be consume within three months from the date of manufacturing

Safety:

KI-33 (E7) is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:

2B Pretoria Street, Kolkata-71
 Tel: 91-33-22823744/45/3671
 Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in

Website: www.ddevgroup.in

Works:

Survey No: 24/3, Demni Road, Village-Demni
 Dadra (Dadra & Nagar Haveli)-396230, India
 Tel:91-9909006426

E-mail: dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate
 New Link Road, Andheri (West)
 Mumbai-400053, India

E-mail: mumbai@ddevgroup.in