



Ddev Plastiks Industries Limited

TECHNICAL DATA SHEET

KI – 13 K (FR) LT LA RoRE OR UV: Oil resistance, Low Halogen, Flame Retardant PVC Cable Compound.

Description:

KI – 13 K (FR) LT LA RoRE OR UV is Low Halogen, flame Retardant compound for low temperature Sheathing applications in a wide variety of cables. **KI – 13 K (FR) LT LA RoRE OR UV** is formulated with a high-quality resin with special plasticizers, stabilizers and flame-retardant chemicals. HCl absorbers are added to reduce the HCl gas emission when the cable burns. PVC compound is resistant to Hydrocarbon (Aliphatic). It is RoHS & REACH compliant.

Specification:

- **IS 5831: 2001** Type ST – II
- **BS 7655 : 1997** Type 9

Colour: Natural/as per requirement

Typical Properties:

Property	Unit	Test Method	Typical Value
Application temperature			(-) 40°C to (+) 90°C
Sp. Gravity @27°C		ASTM - D – 792	1.45 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	87 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60)	≥ 100
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7)	≥ 14.0
Elongation at Break (E.B) @27°C	%	IS : 10810 (7)	≥ 200
Ageing Test	Temperature	°C	100 ± 2
	Duration	Hr	168
Variation of T.S	%	IS : 10810 (11)	≤ ± 25.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 25.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 1.50
Limiting Oxygen Index	%	IS : 10810 (58)	≥ 29.0
Temperature Index	°C	IS : 10810 (64)	≥ 250
Halogen Acid Gas Emission	%	IS : 10810 (59)	≤ 20.0

1. **Oil ageing:**(IRM 902) @ 70°C / 4 hrs – Retention of T.S. & E.B.= 70%

* Test specimen made after milling the granules and then in compression molded at 160 °C for 10 min with 200kg / cm² hydraulic pressure

Above Values are Typical value of Compound and customer need to check before accepting the TDS.

Processing:

KI-13K (FR) LT LA RORE OR UV can be processed on any good extruder designed for PVC at temperature in the range of 140°C- 180°C.This is the guideline temperature range; actual temperature should be determined by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 80+/-5°C is always advisable for better processing.

Packaging:

KI-13K (FR) LT LA RORE OR UV is available in the form of free-flowing pellets and supplied in green color bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage:

Material should be store in moisture free cool & dry place and should be consume within three months from the date of manufacture.

Safety:

KI-13K (FR) LT LA RORE OR UV is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:

2B Pretoria Street, Kolkata-71
Tel: 91-33-22823744/45/3671
Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in

Website: www.ddevgroup.in

Works:

Survey No: 24/3, Demni Road, Village-Demni
Dadra (Dadra & Nagar Haveli)-396230, India
Tel:91-9909006426

E-mail: dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate
New Link Road, Andheri (West)
Mumbai-400053, India

E-mail: mumbai@ddevgroup.in

