An ISO 9001:2015 company **TECHNICAL DATA** 

Peroxide Based XLPE Compound For Continuous Vulcanization Line: KI – XL – 8511E

### **DESCRIPTION:**

KI-XL-8511E is a low density, cross-linkable (peroxide based) polyethylene compound developed specially for continuous Vulcanization process to produce medium voltage power cables (up to 11 KV). It contains low level of contamination; proper balance of anti-oxidant to ensures thermal stability during and after extrusion.

# **SPECIFICATIONS:**

KI-XL-8511E compound meets requirements as applicable under following standards, when processed using sound extrusion practice and testing procedure;

- IEC 60502
- IEC 60840
- IS 7098-II

### **TYPICAL PROPERTIES:**

Property	Unit	Typical Value	Test Method
Density	gm / cm <sup>3</sup>	0.920	ASTM-D-792
Tensile Strength	MPa	15	ASTM D-638
Elongation at break	%	500	ASTM D-638
Hot elongation @200°C, 20N/cm <sup>2</sup>	%	80	IEC-60811-507
Permanent Set after 5 Min.	%	0	IEC-60811-507
Variation in Tensile Strength*	%	± 20	IEC-60811-401
Variation in elongation at break*	%	± 20	IEC-60811-401
Contamination	No./1000 g. granules	<200μ<500μ>500μ 20-5-0	By Optical
			Control Systems
			(KIIL)

<sup>\*</sup> After Heat Ageing at 135°C for 168 hrs. On moulded sheet at 180°C / 20 min.

# **ELECTRICAL PROPERTIES:**

Property	Unit	Typical Value	Test Method
Di-Electric Constant @25°C	-	2.3	ASTM-D-150
Dissipation Factor @25°C	-	0.0004	ASTM-D-150
Di-electric Strength	KV/mm	23	ASTM-D-149
DC Volume Resistivity @ 25°C	Ohm-cm	$1 \times 10^{16}$	ASTM-D-257

MKT: TDS - 8511E - 04/2022

# **PROCESSING GUIDELINES:**

During extrusion in a typical CCV line, following temperature profile is suggested.

Position	Temperature (°C)	
Barrel	95 – 115	
Head	115	
Die	115	
Screw	90	

PACKAGE: 450 / 600 / 875 Kg in PE Liner and Corrugated Paper boxes.

**STORAGE** : Storage shall take place indoors at temperature not generally exceeding 25°C. Box should be kept away from direct sunlight and weathering.

The information given in the document is believed to be reliable and is given in the good faith but without warranty. The user should test the product to ascertain the suitability for the intended use. Product specification or the whole document is subject to change without any prior notice.