

Ddev Plastiks Industries Limited

TECHNICAL DATA SHEET



KI-85FR: Flame Retardant PVC Cable Compound

Description:

KI – 85FR is a Flame Retardant Compound for insulation applications in a wide variety of cables. **KI – 85FR** is formulated with a high quality resin with plasticizers, stabilizers, flame retardant chemicals and other additives.

Specification:

- IS 5831: 2001 Type A (FR) , BS 7655 Section-3.1 : 1997 TI-1

Typical Properties:

Property	Unit	Test Method	Typical Value
Sp. Gravity @27 ^o C		ASTM - D – 792	1.44 ± 0.03
Hardness @27 ^o C	Shore A	ASTM - D 2240	89±2
Thermal Stability@200 ^o C	Minutes	IS : 10810 (60)	≥ 110
Tensile Strength (TS) @27 ^o C	MPa	IS : 10810 (7)	≥ 16.0
Elongation at Break (E.B) @27 ^o C	%	IS : 10810 (7)	≥ 250
Ageing Test	Temperature		80
	Duration		168
Variation of T.S	%	IS : 10810 (11)	≤ ± 15.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 15.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 1.50
Volume Resistivity @27 ^o C	Ohm - cm	IS : 3396 / 79	≥ 1x10 ¹⁴
Limiting Oxygen Index	%	IS : 10810 (58)	≥ 29.0

* Test specimen made after milling the granules and then in compression mould at 160 °C for 10 min with 200kg/cm² hydraulic pressure

Processing:

KI – 85FR can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 140^oC- 180^oC. This is the guideline temperature range, actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 80+/-5^oC for 10minutes is always advisable for better processing.

Packaging:

KI – 85FR is available in the form of free flowing Pellets and packed in 25 kg HDPE woven sacks with inner liner to ensuring prevention from uptake of moisture and contamination.

Storage and Shelf Life:

Material should be store in moisture free cool & dry place and should be consume within three months from the date of manufacturing.

Safety:

KI – 85FR is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information pl contact at;

Head Office:
2B Pretoria Street, Kolkata-01
Tel: 91-33-22823744/45/3671
Fax:91-33-22823739
E-mail: kolkata@Kkalpana.co.in
Website: www.Kkalpanagroup.com

Works:
Survey No: 24/3, Demni Road, Village-Demni
Dadra(Dadra & Nagar Haveli)-396230, India
Tel:91-260-2668 758/59/61,Fax:91-260 2668760
E-mail:dadra@Kkalpana.co.in

168-151-158, Dabhel Industrial Co-Op Soc. Ltd
Dabhel, Daman-369215
Tel: 91-260-2242684/6545123, Fax: 91-260 2243799
E-mail: daman@Kkalpana.co.in

Mumbai Office
106, Laxmi Plaza, Laxmi Industrial Estate
New Link Road, Andheri(West)
Mumbai-400053, India
E-mail: mumbai@Kkalpana.co.in

KOLKATA WORKS
Vill & P.O:Chaturbhujkathi, kandua,
P.S.Sankarail, howrah-711313
E-mail: kolkata@kcalpana.co.in