

TECHNICAL DATA SHEET

KI – 90 FR: Flame retardant PVC Cable Compound(TI-3 /TM3 as per BS 7655)

Description:

KI – 90FR is a heat resistant flame retardant compound for insulation applications in a wide variety of cables.
KI – 90FR is formulated with a high quality resin with plasticizers, stabilizers and flame retardant chemicals.

Typical Properties:

Cable manufactured with **KI – 90FR** according to standard manufacturing process meets BS: 7655 specification.

Property	Unit	Test Method	KI – 90FR
Sp. Gravity @27°C		ASTM - D – 792	1.39 ± 0.03
Hardness @27°C	Shore A	ASTM - D 2240	92 ± 2
Thermal Stability@200°C	Minutes	IS : 10810 (60)	≥ 240
Tensile Strength (TS) @27°C	MPa	IS : 10810 (7)	≥ 15.0
Elongation at Break (E.B) @27°C	%	IS : 10810 (7)	≥ 200
Ageing Test	Temperature	°C	135
	Duration	Hr	336
Variation of T.S	%	IS : 10810 (11)	≤ ± 25.0
Variation of E.B	%	IS : 10810 (11)	≤ ± 35.0
Mass Loss on Ageing	mg/cm ²	IS : 10810 (10)	≤ 1.15
Volume Resistivity @27°C	Ohm - cm	IS : 3396 / 79	≥ 1x10 ¹⁴
Limiting Oxygen Index	%	IS : 10810 (58)	≥ 29.0
Temperature Index	°C	IS : 10810 (64)	≥ 250

* Test specimen made after milling the granules and the compression moulded at 160 °C for 10 min with 200kg / cm² hydraulic pressure

Processing:

KI – 90FR can be processed on any good extruder designed for PVC cable extrusion at temperature in the range of 140°C- 180°C. This is the guideline temperature range, actual temperature should be optimized by the user depending upon the other processing variables. The screw must have a good homogenizing capacity. Preheating of granules at 80+/-5°C is always advisable for better processing.

Packaging:

KI – 90FR is available in the form of free flowing pellets and supplied in bags with sealed double layer PE liner to prevent moisture. The finished bag weight is either 25 kg woven sacks bag or in 1000kg jumbo bags.

Storage:

Material should be store in moisture free cool & dry place.

Safety:

KI – 90FR is not classified as a dangerous product group.

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. These are all the typical values only and subject to change without prior intimation. The product is sold upon condition that purchaser should make their own tests to determine the suitability of such product of their particular purpose and purchasers assume all risks and liability for the results of the use of the product.

For more information PI contact at;

Head Office:

2B Pretoria Street, Kolkata-01
 Tel: 91-33-22823744/45/3671
 Fax:91-33-22823739

E-mail: kolkata@ddevgroup.in

Works:

Survey No: 24/3, Demni Road, Village-Demni
 Dadra(Dadra & Nagar Haveli)-396230, India
 Tel:91-260-2668 758/59/61,Fax:91-260 2668760

E-mail: dadra@ddevgroup.in

Mumbai Office

106, Laxmi Plaza, Laxmi Industrial Estate
 New Link Road, Andheri(West)
 Mumbai-400053, India

E-mail: mumbai@ddevgroup.in

Website: www.ddevgroup.in